

Dry Lean Concrete 350 KSC Cylinder (or 400 KSC Cube) M404



**Convenient
Saves Time
Strong**

Post work, Beam and Foundation Post

Product Characteristic

M404 ready mixed mortar is suitable for concrete work. After mixing with recommended ratio with water, it can be used without addition of any other additives and the concrete work will have compressive strength of minimum 350 KSC.

Instruction for mortar preparation

1. Mix 1 bag (50kg) of TPI M 404 with 7-8 liters of clean water.
2. Mix well until the mixture is homogeneous, and apply according to the common practices for concrete work .
3. In case a special concrete mix with desired properties is required by addition of admixtures, then user can add the additives according to the ratio and procedures given by the manufacturer of the additive.

Usage Quantities

Mixing ratio per bag	Amount per cubic meter
TPI M404 1 bag (50 kg)	TPI M404 45 bag (2,250 kg)
Water 7 - 8 liters	Water 315 - 360 liters

Usage Quantities : In case of mixing with stone size 1/2" or 3/4"

Mixing ratio per bag	Amount per cubic meter
TPI M404 1 bag (50 kg)	TPI M404 30 bag (1,500 kg)
Stone size 1/2" or 3/4" 30kg (3 buckets)	Stone size 1/2" or 3/4" 900 kg (90 buckets)
Water 7-8 liters	Water 210 - 240 liters

Application

Suitable for common small concrete works such as ground leveling, road construction, car park, reinforced concrete construction etc.



Suitable for Post work, Beam and Foundation Post at compressive strength 350 KSC (or 320 KSC Cube)